KutGard Cut Score Matrix

EN388 Cut Score				0	1			2			3						4									5																+
ASTM F1790 Cut Score				0	120	200	250	300	400	500	501	600	700	800	900	1000	1001	1100	1200	1300	1400	1500	1501	1750	2000	2250	2500	2750	3000	3250	3500	3501	3750	4000	4250	4500	4750	5000	5250	5500	5750	6000 +
ITEM	**Method**	**ASTM Score**	**Date**																																							
KutGard Kevlar Gloves																																										
07-K320	ASTM	690							X																																	
07-K200	ASTM	600										X																														
07-K259	ASTM	850													X																											
07-K300	ASTM	850													X																											
07-K350	ASTM	1211																	X																							
KutGard Kevlar Gloves w/Dots																																										
08-K252	ASTM	690							X																																	
08-K200PD	ASTM	600										X																														
08-K200PDD	ASTM	600										X																														
08-K259PDD	ASTM	850													X																											
08-K300PD	ASTM	850													X																											
08-K350PDD	ASTM	1215																	X																							
08-K300PS	ASTM	813												X																												
08-K385	ASTM	3612	J-08																														X									
Kevlar Gloves w/Palm Coating																																										
09-K1300	ASTM	1550																					X																			
09-K1310	ASTM	1262	S-06																	X																						
09-K1400	ASTM	927	J-08													X																										
09-K1450	ASTM	623	M-10									X																														
09-K1444	ASTM	1266	S-08																	X																						
09-K1650	ASTM	717	S-08										X																													
Kevlar Lined Goatskin Driver																																										
09-K3700	ASTM	779	O-07										X																													
KutGard Kevlar Gloves w/Lea. Palm																																										
09-K300LP	ASTM	1631	D-05																					X																		
09-K350LP	EN388																								X																	
Kut-Gard Tube Knit Kevlar Sleeves - All lengths																																										
10-KS (2 Ply)	ASTM	1263	A-08																	X																						
10-KS (Single Ply)	ASTM	675	A-08									x																														
10-KS (2 Ply Kevlar/Cotton)	ASTM	675	A-08									x																														
Kut-Gard Fabric Kevlar Sleeves - All lengths																																										
10-K462X (22" & 26")	ASTM	544	A-08									X																														
10-K472X (22" & 26")	ASTM	375	A-08						X																																	
10-K482X (22" & 26")	ASTM	507	A-08								X																															
KutGard Nuaramid Gloves																																										
12-250	ASTM	1223	N-04																X																							
12-350	ASTM	871													X																											
12-360	ASTM	871													X																											
12-450	ASTM	1353	N-04																		X																					
12-280	ASTM	1913	N-04																						X																	
13-280	ASTM	1961	N-04																						X																	
14-289	ASTM	2300	N-05																								X															

The cut score data represented here is determined using either ASTM F1790 or the EN388 test methods. The resulting score is represented in grams of force required to cut fabric. The ASTM score is clearly stated in the column titled ASTM Cut Score and is plotted on the row of the product. The shaded areas represent the cut score range used to rate cut resistance according to EN388. So to determine the EN388 rating, simply locate the “X” on the row of the product and move to the top of that column to find the EN cut score rating associated with that product.

PROTECTIVE INDUSTRIAL PRODUCTS

KutGard Cut Score Matrix

EN388 Cut Score				0	1			2			3						4					5																		+
ASTM F1790 Cut Score				0	120	200	250	300	400	500	501	600	700	800	900	1000	1001	1100	1200	1300	1400	1500	1501	1750	2000	2250	2500	2750	3000	3250	3500	3501	3750	4000	4250	4500	4750	5000	5250	5500	5750	6000 +
KutGard Dyneema Gloves																																									
17-D200	ASTM	650										X																													
17-D300	ASTM	900													X																										
17-D350	ASTM	1250																	X																						
17-SD200	ASTM	482	F-09						X																																
17-SD300	ASTM	738	F-09										X																												
17-SD325	ASTM	923	F-09													X				X																					
17-SDG325	ASTM	879	F-09												X					X																					
17-SD350	ASTM	937	F-09													X				X																					
17-DL200	ASTM	650										X																													
17-DL300	ASTM	1100																X																							
Kut-Gard Dyneema Sleeves - All lengths																																									
20-D	ASTM	742	D-05										X																												
20-SD	ASTM	570	A-07									X																													
20-TG (2 Ply Tube Knit)	ASTM	853	A-08												X																										
Kut-Gard Dyneema Slabbers																																									
18-SD385-L	ASTM	3700	A-09																														X								
Gtek Dyneema Gloves w/Coating																																									
18-570	ASTM	766											X																												
19-D150	ASTM	610	D-05									X																													
19-D470	EN388		M-06																						X																
19-D475	EN388		M-08																						X																
19-D622 *GREAT WHITE™*	ASTM	501	N-07								X																														
19-D625	ASTM	440	A-07						X																																
19-D650	ASTM	520	A-07								X																														
19-D655	ASTM	537	A-07								X																														
19-D660	ASTM	510	A-07								X																														
19-D434	ASTM	552	A-07								X																														
19-D750	ASTM	561	A-07								X																														
19-D813	ASTM	2,731	A-07																								X														
19-D815	ASTM	538	A-07							X																															
19-D855	ASTM	510	A-07								X																														
KutGard Steel Core Gloves																																									
22-600	ASTM	6600																																							X
22-650	ASTM	4800																																				X			
22-690	ASTM	5000																																					X		
22-710	ASTM	2750																										X													
22-720	ASTM	3700																															X								
22-730	ASTM	2000																							X																
22-750	ASTM	3800																															X								
22-750G	ASTM	4000																																X							
22-754	ASTM	1750																						X																	
22-760	ASTM	4000																																X							
22-760G	ASTM	4000																																X							
22-770	ASTM	3800																															X								
22-780	ASTM	7000+																																							X
22-900	ASTM	4400																																		X					
KutGard Steel Core Sleeves																																									
25-612,618,621	ASTM	6600																																							X
PVC W/ Seamless Kevlar Liner																																									
58-8658K	ASTM	1,177																	X																						X

The cut score data represented here is determined using either ASTM F1790 or the EN388 test methods. The resulting score is represented in grams of force required to cut fabric. The ASTM score is clearly stated in the column titled ASTM Cut Score and is plotted on the row of the product. The shaded areas represent the cut score range used to rate cut resistance according to EN388. So to determine the EN388 rating, simply locate the “X” on the row of the product and move to the top of that column to find the EN cut score rating associated with that product.